

## POLITHERM 26 R SM PINK 80576 MA

**PRODUCT:** 14022137

**DESCRIPTION / USES:** Metallic parts coating for outdoor use.

**CHARACTERISTICS:** 

Resin:PolyesterSpecific gravity: $1,57 \pm 0,10 \text{ g/cm}^3$ Stability:12 month (max. 30°C)

Observations: Free of heavy metals according to RoHS Directive

2002/95/CE of 01/27/2003

**APPLICATION CHARACTERISTICS:** 

Surface:Ferrous and non-ferrousSurface preparation:Ferrous : Phosphatization

Non-ferrous: Chromatization or phosphatization\*

Cure conditions: 10 minutes at 200 °C\*\*

Thickness:  $60 - 80 \mu m$ Application system: Electrostatic gun

**AFTER CURE CHARACTERISTICS:\*\*\*** 

TEST METHOD SPECIFICATION

ADHESION WPS-3905 : GR0 GLOSS @  $60^\circ$  WPS-3854 :  $30 \pm 3$  UB IMPACT (REVERSE) WPS-4130 : Min 50 kg X cm FLEXIBILITY (CONIC MANDREL) WPS-4856 : Max 3 mm

## **CHEMICAL RESISTANCE \*\*\***

**Salt spray:** : Min. 500 h (ASTM B117 – 03)

Humidity: : Min. 1000 h (35°C)

**IMPORTANT:** This coating, when properly applied and cured is suitable for the use of adhesives and sealants. However, because of the different products on the market, it requires prior testing by the user in order to select the adhesive and / or sealant appropriate.

If is not possible the use of the product according to the directions given above we ask you to contact our technical service.

STORAGE: Fresh, dry and covered place.

## COPY FOR INFORMATION

Rua Dr. Ulysses Guimarães, 918 - Fone: +55 (11) 4547-6100 - CEP 09372-050 - Mauá - SP EMERGÊNCIA: (+55) 0800 720 8000 - E-mail: <a href="mailto:tintas@weg.net">tintas@weg.net</a> - www.weg.net Page 1 of 1

Review: 00 Date: 05/25/17

<sup>\*</sup> For non-ferrous metals phosphatizing, please contact our technical service.

<sup>\*\*</sup> After stabilization on correct temperature (metal temperature).

<sup>\*\*\*</sup> The tests were conducted on degreased steel panels in accordance with the cure and thickness specifications. The results may vary, depending on the surface characteristics. For chemical resistance testing, panels were degreased and treated with tricationic phosphat.