

POLITHERM 50 HB R TX BLUE RAL 5013 BR

PRODUCT: 17021577

DESCRIPTION / USES: Metallic parts coating for indoor use.

CHARACTERISTICS:

Resin:Epoxy / PolyesterSpecific gravity: $1,61 \pm 0,10 \text{ g/cm}^3$ Stability: $12 \text{ month (max. } 30^{\circ}\text{C)}$

Observations: Free of heavy metals and other substances provided for in Directive

2015/863 EU of 03/31/2015 (RoHS).

APPLICATION CHARACTERISTICS:

Surface: Ferrous and non-ferrous

Surface preparation: Ferrous : Phosphatization

Non-ferrous: Chromatization or phosphatization*

 Cure conditions:
 10 minutes at 200°C

 Thickness:
 120 - 140 μm

 Application system:
 Electrostatic gun

AFTER CURE CHARACTERISTICS:***

TEST	METHOD	SPECIFICATION
ADHESION	ASTM D 3359	Maximum GR0
GLOSS @ 60°	ASTM D 523	Visual standard
IMPACT (REVERSE)	ASTM 2794	Minimum 40 kg.cm
FLEXIBILITY (CONIC MANDREL)	ASTM D 790 / ISO 178	Minimum 5 mm

CHEMICAL RESISTANCE ***

Salt spray: Minimum 500 h (ASTM B117 – 03)

Humidity: Minimum 1000 h (35°C)

IMPORTANT: If is not possible the use of the product according to the directions given above we ask you to contact our technical service.

STORAGE: Fresh, dry and covered place.

COPY FOR INFORMATION

Review: 0 Date: 13/12/2022

^{*} For non-ferrous metals phosphatizing, please contact our technical service.

^{**} After stabilization on correct temperature (metal temperature).

^{***} The tests were conducted on degreased steel panels in accordance with the cure and thickness specifications. The figures may be change, depending on the surface characteristics. For chemical resistance tests the panels were degreased and treated with tricationic phosphat.