

## W-POXI ZINCO

<b>PRODUCT DESCRIPTION:</b>	Two-component polyamide epoxy primer, rich in zinc. Provides cathodic protection to the substrate.			
<b>RECOMMENDED USES:</b>	Recommended as anti-corrosion primer in structures and equipment exposed to aggressive environments.			
<b>CERTIFICATIONS AND APPROVAL:</b>	This product, when supplied to comply with the RoHs Directive (Restriction of Certain Hazardous Substances) has the letter R in its description.			
<b>PACKAGING:</b>	<b>Component</b>	<b>Content</b>	<b>Package</b>	<b>Unit of measurement</b>
	Component A	3	3,6	L
	Component B	3	3,6	L

<b>CHARACTERISTICS:</b>	<b>Color:</b>	Gray		
	<b>Gloss:</b>	Matte		
	<b>Volume solid:</b>	57 ± 3% (ISO 3233).		
	<b>Shelf-Life:</b>	06 months at 25°C		
	<b>Thickness per coat (dry):</b>	60 µm –65 µm		
	<b>Theoretical coverage:</b>	8,7 m <sup>2</sup> /l without dilution in the thickness of 65 µm dry. Without considering loss factors in application.		
	<b>Resistance to dry heat:</b>	Maximum temperature 120 °C . The product retains its physical and chemical properties up to the temperature of 120 °C however, variations in the coating color and gloss may occur from 60 °C.		
	<b>Drying:</b>			
		<b>10°C</b>	<b>25°C</b>	<b>35°C</b>
	<b>Touch:</b>	180 minutes	90 minutes	1 hour
	<b>Handling:</b>	10 hours	6 hours	5 hours
	<b>Final:</b>	240 hours	168 hours	168 hours
	<b>Overcoating Drying:</b>			
		<b>10°C</b>	<b>25°C</b>	<b>35°C</b>
	Min	12 hours	8 hours	6 hours
	Max	55 hours	48 hours	24 hours

<b>SURFACE PREPARATION</b>	<p>The performance of this product depends on the degree of surface preparation.</p> <p>The surface must be clean, dry and free of any contaminants. Completely remove oils, greases and fats, as described in the SSPC-SP 1 standard.</p> <p>The accumulated dirt must be removed using a dry brush, clean and dry cloth, compressed air blow, vacuum cleaner and/or with the combination of such items, and the soluble salts must be removed through wash with a great quantity of fresh water, preferably with low pressure (up to 5,000 psi) according to SSPC-SP 12/NACE No. 5.</p> <p><b>Surface treatment through Abrasive Blasting process</b></p> <p>Execute the abrasive blasting to near white metal, Sa 2 ½ grade of the ISO 8501-1 visual standard (A Sa 2 ½, B Sa 2 ½, C Sa 2 ½ and D Sa 2 ½) or according to SSPC-SP 10/NACE No. 2, SSPC-VIS 1 visual standard (A SP 10, B SP 10, C SP 10, D SP 10, G1 SP 10, G2 SP 10, G3 SP 10).</p> <p>Inspect the newly blasted surface observing the presence of surface flaws that could become apparent after this stage, adopting appropriate actions to mitigate such defects through grinding, weld filling and/or epoxy putty.</p>
----------------------------	---

It is recommended a roughness profile between 40 and 85 µm.

**For further information, consult WEG Technical Department.**

## PREPARATION FOR APPLICATION

### Mixture

The application should only be made with equipment that has mechanical stirring throughout the process.

Homogenize the contents of each component with mechanical or pneumatic stirring (A and B). Check there are no sediment settled at the bottom of the package. Add component B to component A, at the recommended proportion (volume), under stirring, until complete homogenization, observing the mixing ratio.

### Mixing ratio (Volume)

1 A X 1 B.

### Diluent

#### Epoxy diluent 3005

### Dilution

Depending on the application method, dilute at most 10%

Only add the diluent after complete mixing of components A + B.

Do not dilute with solvents that are not allowed by local legislation and do not exceed the recommended dilution percentage.

Excessive dilution of the coating may affect the formation and aspect of the film and not allow to reach the specified thickness.

### Pot life of the mixture (25°C)

4 h

### Induction time (25°C)

Wait 15 to 20 minutes before application.

In hot areas, we recommend consulting WEG Technical Department.

## APPLICATION FORMS

**The data below is a guide, and similar equipment may be used.**

Changes in nozzle sizes and pressures may be necessary to improve spraying characteristics. Before application, check the equipment and its components are clean and in best condition. Purge the compressed air line to prevent contamination of the coating.

After mixing 2-pack products, if there are stops in the application, and pot life is exceeded (the coating shows variation in fluidity) it can no longer be diluted for further application.

Recoat all sharp edges, cracks and weld beads with a brush to prevent premature failures in these areas.

### Conventional gun:

Gun:	JGA 502/3 Devilbiss or equivalent
Fluid nozzle:	EX
Air cap:	704
Atomization pressure:	60 - 65 psi
Pressure in the tank:	10 - 20 psi
Dilution:	10%

### Airless Gun:

Use Airless:	Use at least pump 60: 1
Fluid pressure:	2500 – 3500 psi
Hose:	¼" internal diameter
Nozzle:	0,019" - 0,023"
Filter:	Mesh 60

Dilution: Max. 5%

### Brush:

Only recommended for touch up small areas or stripe coat (screws, nuts, weld and sharp edges). Use a brush 75 to 100 mm wide for larger surfaces and 25 to 38 mm for touch up. **NOTE:** For application by cutting it may be necessary to apply two or more passes to obtain a uniform layer according to the film

thickness recommended by others.

**NOTE:**

**Cleaning the equipment:**

Epoxy diluent 3005

Do not leave material in the hoses, spray guns and equipment used in the spraying. Thoroughly wash all equipment used.

**PERFORMANCE IN THE APPLICATION**

For a good performance of the product, we recommend following the directions below:

Product not recommended for painting the interior of tanks

In paintings carried out in front of the sea, if exposed to sea air, we recommend to wash with fresh water between coats eliminating settled impurities.

Do not apply the product after the pot life has expired.

We recommend coating only if the surface temperature is at least 3 °C above the dew point temperature.

Variations in color, aspect and gloss (more noticeable in dark colors) may occur, as well as delay in curing and low coating performance, when applied during periods of high air relative humidity, rainy days, low temperatures or drying the coating outdoor.

The temperature of the substrate, the weather and environmental conditions during the application and during the curing of the product, and the thickness of the coat may interfere in the product drying time.

Epoxy systems may have longer curing time when exposed to low temperatures. For temperatures below 10 °C, consult WEG Technical Department.

For better application properties, the coating temperature should be between 21 - 27 °C prior to the mixing and application.

It should not be applied under adverse conditions, such as air relative humidity (RH) above 85%, as changes in color and appearance may occur.

Epoxy-based products are known to have excellent anti-corrosion properties and low resistance to sunlight exposure. In situations of exposure of the film to the weather, over time it will present a loss of gloss known as chalking and its shade will change as a consequence. Remember that even undergoing such chalking, the film anti-corrosion protection is not impaired.

Remember that even with this calcination, the film is not affected in terms of its protection. On newly painted surfaces in direct contact with water during the curing process, localized stains may occur with changes in their color (more visible in dark colors), delay in curing and compromised product performance.

On newly painted surfaces in direct contact with water during the curing process, localized stains may occur with changes in their color (more visible in dark colors), delay in curing and compromised product performance.

In coatings with variation in application method in the same job, the final aspect and gloss of the painted surfaces may show differences.

The application should only be made with equipment that has mechanical stirring throughout the process.

For further information, consult WEG Technical Department.

**SAFETY PRECAUTIONS**

Product developed for industrial use intended for handling by qualified professionals.

Please read carefully all the information contained in the MSDS of this product, available at: [www.weg.net](http://www.weg.net).

Store in a covered, well-ventilated area. Keep the container tightly closed and away from sources of heat or ignition.

Use only in well-ventilated areas avoiding the accumulation of flammable vapors. Keep the product away from heat and sources of ignition.

Do not inhale mists / vapors / aerosols generated during handling and / or application.

Wear protective gloves / protective clothing / eye protection / face protection.

Avoid release this product and its packaging, as well as materials used during handling and application in the environment.

**NOTE:**

The information contained in this technical datasheet is based upon the experience and knowledge acquired in the field by the technical team of WEG.

If using the product without previous inquiry to WEG Coating concerning its suitability for the customer's intended purpose, the customer is aware that the use shall be its exclusive responsibility, WEG not being

responsible for behavior, safety, suitability or durability of the product.

Some information contained in this datasheet are estimated, and can undergo variances arising from factors outside the manufacturer's control. Thus, WEG does not guarantee and does not assume any responsibility regarding the yield, performance or any other material or personal damage resulting from the incorrect use of the products concerned or the information contained in this Technical datasheet.

The information contained in this technical datasheet is subject to periodic modification, without prior notice, due to the policy of evolution and continuous improvement of our products and services, providing solutions with quality to satisfy our customers' requirements.

