

# W-CAR BASE COAT

**PRODUCT INFORMATION:** Single component basecoat based on polyester resin. Available in smooth, metallic and pearl colors. It composes a double layer coating system, applying polyurethane clear coat over the basecoat.

**RECOMMENDED USE:** Recommended for general, partial and touch ups paintings in automotive vehicles.

	<b>Hardener</b>	-	
	<b>Mixing Ratio (Volume)</b>	-	
	<b>Dilution</b>	Ready for use	
	<b>Application Viscosity (25°C)</b>	-	
	<b>Mixture's Operating Life - Pot Life (25°C)</b>	-	
	<b>Equipment</b>	Gravity feed spray gun/ Standard spray gun Air pressure: 40 to 50 psi Spray Nozzle: 1.4 to 1.6 mm	
	<b>Application</b>	Apply 3 to 5 passes with interval of 5 to 10 minutes. 15 to 20 microns total dry thickness.	
	<b>Drying Time</b>	<b>Air:</b> 20 to 30 minutes for clear coat application	<b>Oven:</b> -
	<b>Sanding</b>	-	
	<b>Additivition</b>	-	

**CÓPY FOR INFORMATION**

**WEG TINTAS LTDA - CNPJ 12.006.058/0001-21**

Matriz: Rodovia BR 280, Km 50 - Fone: (+55) (47) 3276-4000 - Fax: (+55) (47) 3276-5500 - CEP 89270-000 - Guaramirim – SC

**PAUMAR S.A. INDÚSTRIA E COMÉRCIO – CNPJ 60.621.141/0001-53**

Rua Dr. Ulysses Guimarães, 918 - Fone: +55 (11) 4547-6100 – CEP 09372-050 - Mauá – SP

EMERGÊNCIA: (+55) 0800 720 8000 - E-mail: [tintas@weg.net](mailto:tintas@weg.net) - [www.weg.net](http://www.weg.net)

Página 1 de 2

Review: 03

Date:Nov/16

This Data Sheet cancels and replaces older versions and can be updated without prior notice

**TECHNICAL PROCEDURES:**

**Surface Preparation**

Apply over W-MIX PRIMER W10 or other primer recommended by our technical/commercial team.

Proceed with sanding according to primer orientation's Technical Data Sheet.

If dots on the primer appears, use dust catch cloth.

**Application Performance**

Be sure that no sediment has been retained on the bottom of the package.

Respect maximum recommended dilution ratio. Excessive dilution of the paint may affect film formation, appearance and make it difficult to obtain the specified film thickness.

Pressure and size changing on the nozzles may be necessary to improve spraying properties. Before application, be sure that all equipment and its respective components are cleaned and in best conditions.

Drying time may vary according to temperature and thickness of the applied product.

Do not apply the product under adverse conditions as well as relative air humidity above 85%, because it might occur appearance and color changings. Do not apply the product on condensed surfaces.

**SAFETY PRECAUTIONS:**

Before handling this product, it is mandatory a careful reading of all information contained in the Material Safety and Data Sheet (MSDS) of the product.

Further information can be obtained by consulting the Technical Department by phone or e-mail specified in the end of this Data Sheet.

**CÓPY FOR INFORMATION**

**WEG TINTAS LTDA - CNPJ 12.006.058/0001-21**

Matriz: Rodovia BR 280, Km 50 - Fone: (+55) (47) 3276-4000 - Fax: (+55) (47) 3276-5500 - CEP 89270-000 - Guaramirim – SC

**PAUMAR S.A. INDÚSTRIA E COMÉRCIO – CNPJ 60.621.141/0001-53**

Rua Dr. Ulysses Guimarães, 918 - Fone: +55 (11) 4547-6100 – CEP 09372-050 - Mauá – SP

EMERGÊNCIA: (+55) 0800 720 8000 - E-mail: [tintas@weg.net](mailto:tintas@weg.net) - [www.weg.net](http://www.weg.net)

Página 2 de 2

Review: 03

Date:Nov/16

This Data Sheet cancels and replaces older versions and can be updated without prior notice