

W-CAR ANTICORROSIVE SPRAY

PRODUCT INFORMATION: Fast drying, easy sanding anticorrosive primer for small surfaces repair.

RECOMMENDED USE: Recommended for repairing small surfaces with scratches or imperfections; correcting failures over putty or primer; surface repair with ages paints.

COLOR: Grey

	Hardener	-	
	Mixing Ratio (Volume)	-	
	Dilution	Ready for use	
	Application Viscosity (25°C)	-	
	Mixture's Operating Life - Pot Life (25°C)	-	
	Equipment	-	
	Application	Apply 2 to 3 passes with interval of 5 to 10 minutes. 10 to 15 microns of total dry thickness.	
	Drying Time	Air: Touch: 5 – 10 minutes Handling: 15 minutes	Oven: -
	Sanding	Minimum 30 minutes Use sandpaper 600 or 800.	
	Additivation	-	

CÓPY FOR INFORMATION

WEG TINTAS LTDA - CNPJ 12.006.058/0001-21

Matriz: Rodovia BR 280, Km 50 - Fone: (+55) (47) 3276-4000 - Fax: (+55) (47) 3276-5500 - CEP 89270-000 - Guarimirim – SC

PAUMAR S.A. INDÚSTRIA E COMÉRCIO – CNPJ 60.621.141/0001-53

Rua Dr. Ulysses Guimarães, 918 - Fone: +55 (11) 4547-6100 – CEP 09372-050 - Mauá – SP

EMERGÊNCIA: (+55) 0800 720 8000 - E-mail: tintas@weg.net - www.weg.net

Página 1 de 2

Review: 03

Date:Nov/16

This Data Sheet cancels and replaces older versions and can be updated without prior notice

TECHNICAL PROCEDURES:

Surface Preparation

The surface to be coated must be dry and free of impurities as rust, dust, greases oils and any other contaminant that may compromise product performance.

Application Performance

Shake the can well with circle movements before and during application.

Drying time may vary according to temperature and thickness of the applied product.

Do not apply the product under adverse conditions as well as relative air humidity above 85%, because it might occur appearance and color changings. Do not apply the product on condensed surfaces.

SAFETY PRECAUTIONS:

Before handling this product is mandatory a careful reading of all information contained in the Material Safety and Data Sheet (MSDS) of the product.

Further information can be obtained by consulting the Technical Department by phone or e-mail specified in the end of this Data Sheet.

CÓPY FOR INFORMATION

WEG TINTAS LTDA - CNPJ 12.006.058/0001-21

Matriz: Rodovia BR 280, Km 50 - Fone: (+55) (47) 3276-4000 - Fax: (+55) (47) 3276-5500 - CEP 89270-000 - Guaramirim – SC

PAUMAR S.A. INDÚSTRIA E COMÉRCIO – CNPJ 60.621.141/0001-53

Rua Dr. Ulysses Guimarães, 918 - Fone: +55 (11) 4547-6100 – CEP 09372-050 - Mauá – SP

EMERGÊNCIA: (+55) 0800 720 8000 - E-mail: tintas@weg.net - www.weg.net

Página 2 de 2

Date:Nov/16

Review: 03

This Data Sheet cancels and replaces older versions and can be updated without prior notice