

# WEGPOXI BLOCK N 2912 TIPO II ALUMÍNIO

**PRODUCT DESCRIPTION:** High-solids and high-build three-component novolac epoxy primer pigmented with aluminum. It has extremely low content of volatile organic compound (Low VOC). It provides excellent chemical resistance and good resistance to impact. In addition to providing unmatched corrosion protection WEGPOXI BLOCK N 2912 TIPO II has excellent surface hardness and impermeability.

**RECOMMENDED USES:** It can also be used for the exterior of tanks and piping, oil and gas extraction platforms, decks and on-board machinery, as well as for industrial applications and metal structures where corrosion and chemical resistance is essential.

**CERTIFICATIONS AND APPROVAL:** It complies with Petrobras Standard N 2912 - Type II. It complies with Petrobras Standard N 2913. This product, when supplied to comply with the RoHs Directive (Restriction of Certain Hazardous Substances) has the letter R in its description.

PACKAGING:	Component	Content	Package	Unit of measurement
	Component A	2,33	3.6	L
	Component B	0,55	0.9	L
	Component C	0,8 kg	0.9	

**CHARACTERISTICS:**

**Color:** Aluminum

**VOC content:** 60 g/l

**Flash Point:** > 55 °C

**Shelf-Life (25°C):** 12 months

**Theoretical coverage:** 2,56 m<sup>2</sup>/l without dilution in the thickness of 375 µm dry. Without considering loss factors in application.

**Resistance to dry heat:** Maximum temperature 150 °C . The product retains its physical and chemical properties up to the temperature of 150 °C however, variations in the coating color and gloss may occur from 60 °C (140°F).

**Drying:**

	10 °C	25 °C	35 °C
<b>Touch:</b>	14 hours	6 hours	4 hours
<b>Handling:</b>	30 hours	16 hours	8 hours
<b>Final:</b>	240 hours	168 hours	168 hours
<b>Pot Life</b>	2 hours	90 minutes	60 minutes

**Overcoating Drying:**

	10 °C	25 °C	35 °C
Min	10 hours	6 hours	3 hours
Max	30 hours	24 hours	20 hours

**SURFACE PREPARATION**

The performance of this product depends on the degree of surface preparation.

The surface must be clean and free of any contaminants. Completely remove oils, greases and fats, as described in the SSPC-SP 1 standard.

The accumulated dirt must be removed using a dry brush, clean and dry cloth, compressed air blow, vacuum cleaner and/or with the combination of such items, and the soluble salts must be removed through wash with a great quantity of fresh water, preferably with low pressure (up to 5,000 psi) according to SSPC-SP 12/NACE No. 5.

### Surface treatment through the hydroblasting process

Execute hydroblasting (pressure  $\geq 10,000$  psi) according to SSPC-SP standard 12/NACE No. 5, reaching grade WJ-2 (C WJ-2, D WJ-2, E WJ-2, F WJ-2, G WJ-2 and H WJ-2) of the SSPC-VIS 4/NACE VIS 7 visual standard.

This product can be applied to a surface that has been hydroblasted and presents the grade "moderate flash rust", WJ-2 M of the SSPC-VIS 4/NACE VIS 7 visual standard.

Note 2: The high or extremely high hydroblasting does not open an anchor pattern (only if the surface has already been subject to some type of abrasive blasting).

**NOTE 1:** The hydroblasting at extreme high pressure can remove oils and greases from the surface; however, that does not rescind the requirement of the previous degreasing stage.

### Surface treatment through Abrasive Blasting process

Execute the abrasive blasting to near white metal, Sa 2 ½ grade of the ISO 8501-1 visual standard (A Sa 2 ½, B Sa 2 ½, C Sa 2 ½ and D Sa 2 ½) or according to SSPC-SP 10/NACE No. 2, SSPC-VIS 1 visual standard (A SP 10, B SP 10, C SP 10, D SP 10, G1 SP 10, G2 SP 10, G3 SP 10).

It is recommended a roughness profile between 50 and 100  $\mu\text{m}$  (1.97 - 3.94 mils).

Inspect the newly blasted surface observing the presence of surface flaws that could become apparent after this stage, adopting appropriate actions to mitigate such defects through grinding, weld filling and/or epoxy putty.

In case of oxidation on the substrate from the end of the abrasive blasting to the beginning of the coating application, the surface must be blasted again until reaching the specified visual standard.

For areas close to sea air, it is necessary to wash the surface with fresh water at low pressure (minimum 3,000 psi) before the abrasive blasting. And in some cases it is necessary to repeat the washing procedure after the abrasive blasting to remove possible soluble contaminants settled on the surface proceeding with a new abrasive blasting.

The maximum content of soluble impurities on the blasted surface according to the test described in ISO 8502-6 and distilled water must not exceed a measured conductivity according to ISO 8502-9 corresponding to a maximum content of 20  $\text{mg}/\text{cm}^2$  (2  $\mu\text{g}/\text{cm}^2$ ) in immersed or buried areas.

### Surface treatment through the manual mechanical cleaning process

Execute manual mechanical cleaning for carbon steel surfaces that present the oxidation grades C or D, according to the SSPC-VIS 3 visual standard. For surfaces previously painted that present grades E, F or G according to standard SSPC-VIS 3.

**NOTE:** The manual mechanical cleaning process is only recommended for small areas.

**NOTE:** If it is not possible to execute the manual mechanical cleaning process, as an alternative the surface can be prepared with abrasive blasting to near white metal, grade Sa 2½ of the ISO 8501-1 visual standard (C Sa 2½ and D Sa 2½) or according to SSPC-SP 10/NACE No. 2, SSPC-VIS 1 visual standard (C SP 10, D SP 10).

This surface treatment is not recommended for the maintenance of the interior of the tanks.

### Application over primer

If a shop primer is present on the surface, it must be removed with abrasive blasting to near white metal Sa 2 ½ of ISO 8501-1 visual standard or according to SSPC-SP 10/NACE No. 2, SSPC-VIS 1 visual standard.

If it is necessary to use an anti-corrosion primer, which must be approved by Weg technical department. The primer surface must be dry, free of any contaminants.

Observe the primer overcoating interval before applying the product. If the primer overcoating time is exceeded, sand as described in the primer data sheet. In coatings made on a primer after the overcoating interval, the adhesion values according to ASTM D 4541 may present lower values than those specified by Petrobras standard N 2913.

For external coatings where the maximum overcoating interval of the product is exceeded, an anchor pattern must be created using hand or mechanical tools, such as: sandpaper 60 or 80, rotary brush, among others, or brush off, grade Sa 1 of ISO 8501-1 visual standard or in accordance with SSPC-SP 7 / NACE No. 4. For internal coatings, it is only acceptable to create an anchor pattern using brush off, Sa 1 grade of ISO 8501-1 visual standard or according to SSPC-SP 7 / NACE No. 4.

In case of retouching, keep the original coating system.

Small areas that are worn, damaged or the like, must be prepared by abrasive blasting to near white metal Sa 2½ of ISO 8501-1 visual standard or in accordance with SSPC-SP 10 / NACE No. 2, SSPC-VIS 1 visual standard. If it is not possible to execute the abrasive blasting, as an alternative the surface can be prepared with rotary power tools according to grade St 3 of ISO 8501-1 visual standard or according to SSPC-SP 11, and the SSPC-VIS 3 visual standard can be used as an aid.

### Treatment of Steel Carbon Surfaces

Hard superficial layers (for example, layers resulting from flame cut) must be removed by grinding it before beginning the abrasive blasting.

All the welds must be inspected e, if necessary, be repaired before the ending of the abrasive blasting. Porosity, cavities, weld splashes, etc. must be repaired by means of proper mechanical treatment or weld repair; in the other areas, round the sharp edges ( $r \geq 2$  mm, ISO 8501-3).

**For further information, consult WEG Technical Department.**

### PREPARATION FOR APPLICATION

#### Mixture

Homogenize the contents of component A by means of mechanical or pneumatic stirring. Ensure that no sediment is settled at the bottom of the package. Slowly add component A to component C. Slowly homogenize by manual or pneumatic stirring until a homogeneous, lump-free mixture is obtained. Only then add component B. Repeat the homogenization process. The mixing ratio recommended for the preparation of the paint should be observed. If necessary, filter using a 60 mesh screen.

#### Mixing ratio (Volume)

A X B. X C

#### Diluent

#### Dilution

This product should not be diluted. If necessary, consult WEG Technical Department.

#### Induction time (25°C)

No induction time required.

In hot areas, we recommend consulting WEG Technical Department.

### APPLICATION FORMS

**The data below is a guide, and similar equipment may be used.**

In the spray application, make a 50% overlap in each gun pass, concluding with a cross pass. This technique is used to avoid uncovered and unprotected areas and to obtain a suitable aesthetic finish.

Recoat all sharp edges, cracks and weld beads with a brush to prevent premature failures in these areas.

Changes in nozzle sizes and pressures may be necessary to improve spraying characteristics.

Before application, check if the equipment and its components are clean and in best condition.

Purge the compressed air line to prevent contamination of the coating.

After mixing two-component products, if there are stops in the application, and pot life is exceeded (the coating shows variation in fluidity) it can no longer be diluted for further application.

The data below is a guide, and similar equipment may be used.

#### Airless Gun:

Use Airless:  
Fluid pressure:  
Hose:

Use at least pump 60: 1  
3500 – 4500 psi  
¾" internal diameter

Nozzle:  
Note:

0,025" - 0,031"  
The diameter of the fluid hose should not be smaller than ½" with ¾" in the harness, and its length should not exceed 5

meters.

### Brush:

Only recommended for touch up small areas or stripe coat (screws, nuts, weld and sharp edges). Use a brush 75 to 100 mm wide for larger surfaces and 25 to 38 mm for touch up.

### Roller:

Use a thin nap, seamless sheepskin or microfiber roller for epoxy coatings.

For application with brush and/or roller, two or more passes may be necessary to obtain a uniform layer according to the recommended film thickness per coat.

### Cleaning the equipment:

Clean all equipment immediately after use.

### NOTE:

Do not leave catalyzed product in contact with the equipment used in the application, because the coating will vary in fluidity at temperatures above specified in the pot life and will cure faster, making the cleaning difficult.

Furthermore, it is a good working practice to periodically wash the spray equipment along the day. The cleaning frequency will depend on the amount sprayed, temperature and elapsed time, including all delays.

### PERFORMANCE IN THE APPLICATION

For a good performance of the product, we recommend following the directions below:

Variations in color, aspect and gloss (more noticeable in dark colors) may occur, as well as delay in curing and low coating performance, when applied during periods of high air relative humidity, rainy days, low temperatures or drying the coating outdoor.

Epoxy-based products are known by having excellent anti-corrosion properties and low resistance to sunlight exposure. In situations of exposure of the film to the weather, over time it will present a loss of gloss known as chalking and its shade will change as a consequence. Remember that even undergoing such chalking, the film anti-corrosion protection is not impaired.

In paintings carried out in front of the sea, if exposed to sea air, we recommend to wash with fresh water between coats eliminating settled impurities.

The product should be stored at 20°C - 30°C (68°F - 86°F) to achieve viscosity for proper application.

Do not use excessive air pressure. Adjust the fluid pressure and nozzle properly for a better atomization.

Epoxy systems may have longer curing time when exposed to low temperatures. For temperatures below 10 °C (50°F), consult WEG Technical Department.

The product allows the coating over recently hydroblasted surfaces with small traces of flash rust equivalent to the "moderate" grade described in standard SSPC VIS4 (I) / NACE No. 7.

It is not recommended to apply this product over a surface covered with a water film or exposed to rain, neither to expose the freshly painted surface to direct contact with water during the curing process or places with low temperatures or to put the parts to dry outdoors, as staining with changes in color (more noticeable in dark colors), delay in curing and impairment of the product performance may occur.

We recommend coating only if the surface temperature is at least 3°C (37,4°F) above the dew point temperature.

Do not apply the product after the pot life has expired.

For better application properties, the coating temperature should be between 21°C - 27 °C (69.8°F - 80.6 °F) prior to the mixing and application.

In coatings with variation in application method in the same job, the final aspect and gloss of the painted surfaces may show differences.

The temperature of the substrate, the weather and environmental conditions during the application and during the curing of the product, and the thickness of the coat may interfere in the product drying time.

Before application, the weather conditions must be observed: There should be no threat of rain or drizzle. The surface temperature must be at least 3°C (37.4°F) above the dew point and the relative humidity must not exceed 85%.

Under adverse weather conditions indoors and/or outdoors with high relative humidity, rain, or drizzle, low or low temperatures and excessively high temperatures, variations in color and other product characteristics may occur. Consult the WEG Technical Department for more information.

For further information, consult WEG Technical Department.

## SAFETY PRECAUTIONS

Product developed for industrial use intended for handling by qualified professionals.

Please read carefully all the information contained in the MSDS of this product, available at: [www.weg.net](http://www.weg.net).

Store in a covered, well-ventilated area. Keep the container tightly closed and away from sources of heat or ignition.

Use only in well-ventilated areas avoiding the accumulation of flammable vapors. Keep the product away from heat and sources of ignition.

Do not inhale mists / vapors / aerosols generated during handling and / or application.

Wear protective gloves / protective clothing / eye protection / face protection.

Avoid release this product and its packaging, as well as materials used during handling and application in the environment.

## NOTE:

The information contained in this technical datasheet is based upon the experience and knowledge acquired in the field by the technical team of WEG.

If using the product without previous inquiry to WEG Coating concerning its suitability for the customer's intended purpose, the customer is aware that the use shall be its exclusive responsibility, WEG not being responsible for behavior, safety, suitability or durability of the product.

Some information contained in this datasheet are estimated, and can undergo variances arising from factors outside the manufacturer's control. Thus, WEG does not guarantee and does not assume any responsibility regarding the yield, performance or any other material or personal damage resulting from the incorrect use of the products concerned or the information contained in this Technical datasheet.

The information contained in this technical datasheet is subject to periodic modification, without prior notice, due to the policy of evolution and continuous improvement of our products and services, providing solutions with quality to satisfy our customers' requirements.